

FICHA TECNICA

RETRACTIL 400 METROS

Characteristic	Method	Unid.	Direction	12 mic.	Tolerances
Tensile strength	ASTM D882	Mpa	Machine Direction	30,4	± 10 %
			Transversal Direction	15	± 10 %
Elongation at break		%	Machine Direction	290	± 10 %
			Transversal Direction	600	± 10 %
Puncture		Kg	-	2	± 10 %
Guaranteed Prestretch		%	-	140	± 10 %

Composición:

Polietileno Lineal de Baja Densidad PELBD

Roll Format (Formato bobina):

Gross Weight (Peso Bruto): 2226 gr.

Core Weight (Peso Mandril): 250 gr.

Net Weight (Peso Neto): 1976 gr.

Length (meters/roll): 400 meters

***Bobinas de 400 metros lineales de film*

The above values are to be considered as indicative in order to facilitate the choice and usage but are not given for guarantee purposes.